

Appl. No.: 10/814,971

Amendment Dated: March 21, 2007

Reply to Office Action of September 22, 2006

Amendments to the Specification

On Page 28, amend Table 3 as follows:

Chemical		Retention of Elongation at break after two days of exposure (%)		
		75% 75 ppm H ₃ PO ₄	1% epoxy polymer	2% epoxy polymer
	No exposure	100	100	100
Oleic Acid	No strain	71	87	90
	1% strain	4	15	17
Coppertone	No strain	79	96	5
	1% strain	47	2	2
Windex	No strain	83	78	86
	1% strain	5	4	4
Cascade	No strain	89	96	96
	1% strain	Breaks	93	94
Vegetable Oil	No strain	81	92	86
	1% strain	104	50	88